



Density 2.2 pcf (35.2 kg/m<sup>3</sup>)  
Maximum Loading 2.5 psi (17.5 kPa)  
Color Black, Natural



**ETHAFOAM™**  
packaging products

## ETHAFOAM™ 220 Polyethylene Foam

ETHAFOAM™ 220 polyethylene foam is a strong, resilient, medium-density 2.2 pcf (35.2 kg/m<sup>3</sup>), closed-cell foam. It is ideally suited as a component material in products requiring a shock absorbing, vibration dampening, insulating and/or buoyancy component, and as a material for cushioning components in packaging applications for loadings up to 2.5 psi (17.5 kPa).

ETHAFOAM 220 has outstanding recovery characteristics that provide optimal cushioning protection against repeated impacts. It is ideal for cushion packaging and is used in many applications, including computer, automotive, construction and recreation. To achieve optimum performance, Dow recommends that qualified packaging engineers design the total packaging solution.

### Sizes Available in Black (Planks):

2" x 48" x 108"  
4" x 48" x 108"

### Sizes Available in Natural (Planks):

1.5" x 48" x 108"  
2" x 48" x 108"  
2.5" x 48" x 108"  
3" x 48" x 108"  
4" x 24" x 108"  
4" x 48" x 108"

### Product Features

ETHAFOAM™ 220 polyethylene foam is a durable, lightweight, flexible, solid extruded product. As the properties listed on the reverse suggest, ETHAFOAM 220 offers excellent strength, resistance to creep under load, vibration and shock absorbency, and water resistance characteristics.

ETHAFOAM 220 is produced with Dow's patented *RapidRelease* manufacturing process. *RapidRelease* technology delivers a higher quality product with improved dimensional stability and safety. This process technology incorporates a patented CFC- and HCFC-free blowing agent system and an accelerated curing system that reduces residual blowing agents in ETHAFOAM products to trace amounts.

ETHAFOAM 220 meets the requirements of the U.S. Clean Air Act Amendments. It is easily fabricated, impervious to most chemicals, non-abrasive and performs consistently over a wide range of temperatures.

ETHAFOAM 220 is also reusable and completely recyclable because it is made of non-crosslinked polyethylene.

### Flammability

ETHAFOAM™ 220 polyethylene foam has successfully passed FMVSS 302 flammability testing, conducted according to the U.S. Code of Federal Regulations, CFR 49.

**ETHAFOAM**

Product Information

Physical Properties of ETHAFOAM™ 220 Polyethylene Foam			
Physical Properties <sup>1</sup>	Test Method	Direction	Value
Density	ASTM D3575, Suffix W, Method B; ISO 845		pcf (kg/m <sup>3</sup> ) 2.2 (35.2)
Compression Set	ASTM D3575, Suffix B (50% compr.); EN/ISO 1856 (23°C, 25% compr.)	Vertical	< 20% < 10%
Compressive Creep (1000 hrs @ 73°F [23°C])	ASTM D3575, Suffix BB	Vertical	< 10% @ 2.5 psi (17.5 kPa)
Compressive Deflection @ 10% @ 25% @ 50%	ASTM D3575, Suffix D	Average	psi (kPa) 7 (50) 9 (65) 18 (124)
Thermal Stability	ASTM D3575, Suffix S; ISO 2796		< 1.5% < 2%
Thermal Conductivity @ 75°F (24°C) @ 23°F (-5°C)	ASTM D3575, Suffix V; EN 28301; ISO 2581	Vertical	BTU•in/hr•ft <sup>2</sup> •°F (W/m <sup>2</sup> K) 0.42 (0.06) 0.37 (0.05)
Water Absorption	ASTM D3575, Suffix L; ISO 2896; ASTM C272		lb/ft <sup>2</sup> (kg/m <sup>2</sup> ) 0.3 (1.5) < 3% by volume
Buoyancy	ASTM D3575, Suffix AA		pcf (kg/m <sup>3</sup> ) 58 (930)
Tensile Strength @ peak	ASTM D3575, Suffix T; ISO 1798	Average	psi (kPa) 32 (220)
Tensile Elongation	ASTM D3575, Suffix T; ISO 1798	Average	50%
Tear Strength	ASTM D3575, Suffix G	Average	lb/in (N/mm) 10 (1.75)

<sup>1</sup>The data presented for this product are for unfabricated ETHAFOAM polyethylene foam products. While values shown are typical of the product, they should not be construed as specification limits.

*For information on products, design assistance and testing services available from Dow, contact us at: 1-866-PKG-FOAMS (754-3626) or [www.ethafoam.com](http://www.ethafoam.com)*

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

WARNING: ETHAFOAM polyethylene foam products are combustible and may constitute a fire hazard if improperly used or installed. During transportation, storage, installation and use, these products should not be exposed to open flame or other ignition sources.

ETHAFOAM PACKAGING PRODUCTS  
THE DOW CHEMICAL COMPANY  
P.O. Box 1206 • Midland, MI 48641-1206 • USA  
[www.ethafoam.com](http://www.ethafoam.com)

